

Product Data Sheet

Flexible Fibre Adhesive S1

Description

Nicobond Flexible Fibre Adhesive S1 – Highly flexible standard setting wall and floor tile adhesive with fibre reinforcement. A single part, excellent grab, non-slip, polymer enhanced, waterproof and flexible adhesive for fixing ceramic and glass wall and floor tiles, porcelain, mosaic and natural stones in situations where a standard setting adhesive is preferred. May be used in areas where slight vibration occurs. Exceeds requirements of BS EN 12004 and BS EN 12002

Uses

Nicobond Flexible Fibre Adhesive S1 will bond to various substrates :-
 Sand/cement screeds and rendering • Brick and blockwork • Tile backing boards, C.P. Board • Concrete • Plasterboard • Plywood • Glazed surfaces • Flooring grade asphalt • Hard vinyl tiles • Timber floors must be prepared in accordance with BS 5385 and the N&C Nicobond Tiling Solutions brochure.

Features

- Use to fix Porcelain & Marble and Stone
- Use to fix Glass Tiles
- Added Fibres
- Excellent initial grab - non-slip
- Internal and external applications
- Suitable for tiling swimming pools
- Compatible with Under-tile heating

| EN 12004 Test Methods | |
|-----------------------|--|
| EN 1308 | Determination of slip |
| EN 1346 | Determination of open time |
| EN 1347 | Determination of wetting capability |
| EN 1348 | Determination of tensile adhesive strength |
| EN12002 | Determination of transverse deformation |

| Application Data | |
|------------------------------|---|
| Colour | Grey & White |
| Mixing Ratio | Mixing Ratio (water only) Approx 3.5 – 3.7 Vol powder to 1 Vol Clean water. (Approx 20kg to 5.0 litres water) Mixing |
| Mixing | For large quantities, use a Nicobond whisk in a slow speed electric drill and mix to a smooth consistency, use immediately. |
| Consistency of mix | slump resistance mortar |
| Bed thickness | Up to 12 mm (6mm Max for Glass Tiles) |
| Coverage | Notched trowel method 2kg per m ² at 3mm thickness. Solid bed 4kg per m ² at 3mm thickness. |
| Pot Life | Approx 3 hours at 20°C |
| Open Time | Approx 30 minutes at 20°C |
| Adjustability Time | 15 - 20 minutes at 20°C |
| Setting time | Approx 18 – 24 hours at 20°C |
| Grouting After Fixing | Approx 18 - 24 hours at 20°C |
| Ready For Light foot Traffic | Approx 18 - 24 hours at 20°C |
| Installation Temperature | Minimum 5°C - 30 °C |
| Operating Temperature | - 20°C to 100°C |
| Packaging | 20kg 10kg |



The adhesive shall be Nicobond Flexible Fibre Adhesive S1 as manufactured by N&C Building Products Limited, 41-51 Freshwater Road, Chadwell Heath, Romford, Essex, RM8 1SP, England. Tel: 020 8586 4600 and shall be applied strictly in accordance with the Manufacturer's current data sheets and instructions.



Products for the Professional

Nicobond Flexible Fibre Adhesive S1

November 2023

Priming

Sealing and Priming cementitious and other surfaces
– Use Nicobond Primer diluted with water.

Highly Absorbent cementitious surfaces and difficult substrates
– Use Nicobond Primer diluted with water and blended with the cement based product to be used.

Priming of interior gypsum based plaster and timber substrates
– Use Nicobond Universal Bonding Agent and Sealer.

Primers should be used in accordance with the manufacturer's instructions
– refer to Nicobond Primer data sheet.

Surface Preparation

Surfaces to be tiled should be rigid, dimensionally stable, sound, clean and free from laitance, paints, salts, grease, dust and any contamination which may prevent adhesion. It is recommended that any residual quantities of old adhesive be removed to expose approximately 80% of the original substrate, any remaining residues must have a cohesive strength to support the application of any Nicobond product..

Application

Wall Tiling - Thin Bed Method

Spread the prepared adhesive with the straight edge of a Nicobond Notched Trowel to a maximum depth of 3mm. Reverse the Trowel and comb the adhesive with the Notched Edge, ensuring that continuous horizontal ribs of adhesive are formed.

Wall Tiling - Thick Bed Method

Working up to the maximum bed thickness specified for the product spread the prepared adhesive with the straight edge of the Nicobond Notched Trowel. Reverse the Trowel and lightly comb the surface of the adhesive with the notched edge ensuring that continuous, horizontal ribs of adhesive are formed.

In areas of high moisture, or for exterior work, the solid bed fixing method must be used, i.e. no voids behind the tiles.

Floor Tiling Thick Bed Method

The mixed adhesive should be applied with the straight edge of the Nicobond Notched Trowel up to the maximum depth specified for the product. Lightly comb over the surface of the adhesive using the notched edge of the Trowel. Where tiles have deep keys or studs, spread adhesive onto the back of the tile to fill the keys or spaces between studs.

Bonding of the Tiles

Fix dry tiles immediately by pressing them firmly into position with a slight sliding or twisting action. Where appropriate, the adhesive can be spread both onto the surface as described above, and buttered on the backs of the tiles.

Whichever method is used, the tiles should be firmly tamped or pressed home to ensure solid bedding without voids, particularly on flooring installations. Floors should not be opened to traffic until the adhesive has hardened.

From time to time remove a tile to check that full contact has been made with the adhesive bed. Exterior installations must be protected from rain and frost until the adhesive has fully set. Where fixing is carried out in hot conditions, the finished tiling should be protected from direct sunlight to avoid premature drying.

Tile Fixing

Tile fixing should be carried out in accordance with BS 5385 and BS 8000 Codes of Practice for the installation of wall and floor tiles. Movement joints should be inserted in internal corners, at floor perimeters and other locations as recommended in relevant British codes of practice.

For advice on tiling to different substrates refer to the Nicobond Tiling Solutions brochure.

Shelf Life

12 months in unopened bags from the date of packing.

Storage

This product must be clear of the ground stored under dry conditions. Protect from frost.

Cleaning

During application, any residual adhesive must be washed from the face of tiles before it sets.
Wash tools in water immediately after use.

Health & Safety Advice

Nicobond Flexible Fibre Adhesive S1 is classified under the Chemicals (Hazard Information and Packaging for Supply) Regulations. Nicobond Flexible Fibre Adhesive S1 contains cement, contact with water causes an alkaline reaction which may cause skin irritation and/or caustic burns to mucous membranes. Wear suitable protective clothing, gloves and eye/face protection. Keep away from children.

The relevant Material Safety Data Sheet can be obtained from www.ncnicobond.com or directly from N & C Building Products Ltd at the address below.

N & C Building Products Limited
41-51 Freshwater Road
Chadwell Heath
Romford
Essex RM8 1SP
Tel: 020 8586 4600
Fax: 020 8586 4646
Email: info@nichollsandclarke.com
Web: www.ncnicobond.com